



## Garlock WHITE GYLON® 3540

### MATERIAL PROPERTIES\*

<b>Color:</b>	White
<b>Composition:</b>	Microcellular PTFE
<b>Fluid Services<sup>1</sup>:</b>	Strong caustics, strong acids, chlorine, hydrocarbons, cryogenics, glass-lined equipment
<b>Temperature<sup>2</sup>, °F (°C)</b>	
Minimum:	-450 (-268)
Continuous Max:	+500 (+260)
<b>Pressure<sup>2</sup>, Maximum, psig (bar):</b>	1200 (83)
<b>P x T (max.)<sup>2</sup>, psig x °F (bar x °C)</b>	
1/32 and 1/16":	350,000 (12,000)
1/8":	250,000 (8,600)
<b>Flammability:</b>	Will Not Burn
<b>Bacterial Growth:</b>	Will Not Support
<b>Meets Specification:</b>	FDA (Food and Drug Administration)

### TYPICAL PHYSICAL PROPERTIES\*

<b>ASTM F36</b>	<b>Compressibility, %:</b>	70-85
<b>ASTM F36</b>	<b>Recovery, %:</b>	8
<b>ASTM F38</b>	<b>Creep Relaxation, %:</b>	10
<b>ASTM D149</b>	<b>Dielectric Properties, range, volts/mil.</b>	
	Sample conditioning	1/16"      1/8"
	3 hours at 250°F:	86      61
	96 hours at 100% Relative Humidity	16      -
<b>ASTM F586</b>	<b>Design Factors</b>	1/16" & Under      1/8"
	"m" factor:	3.0      3.0
	"y" factor, psi (N/mm <sup>2</sup> ):	1700 (11.7)      2200 (15.2)
<b>ROTT</b>	<b>Gasket Constants, 3/8":</b>	Gb=550      a=0.304      Gs=7.64x10 <sup>-1</sup>
<b>ASTM F104</b>	<b>Line Call Out:</b>	F419000A9B2 <sup>(3)</sup>

### SEALING CHARACTERISTICS\*

	ASTM F37B Fuel A	DIN 3535- 4 Gas Permeability
<b>Gasket Load, psi (N/mm<sup>2</sup>):</b>	1000 (7)	4640 (32)
<b>Internal Pressure, psig (bar):</b>	9.8 (0.7)	580 (40)
<b>Leakage</b>	0.25 ml/hr.	<0.015 cc/min

**Notes:**

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>1</sup> See Garlock chemical resistance guide.

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum P x T, consult Garlock Applications Engineering.

<sup>3</sup> Third cumeral 9: Compressibility = 70-85%. A9: Leakage in Fuel A (Isooctane), Gasket Load = 1,000psi (7.0N/mm<sup>2</sup>), Pressure = 9.8psig (0.7bar): Typical = 0.25ml/hr, Max = 1.0ml/hr.